

BoltaSoft® Marine Upholstery Boat Topping

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	16.3 ± 10%
Total Wt. – oz./lin. yd. (CFFA-700d)	25.0 ± 10%
Width (min.) – in. (CFFA-700a)	54"
Topskin Thickness	.013"
Face Content	PVC

Backing	
Construction	Woven
Content	Polyester
Fiber Type	Spun

Adhesion (CFFA-3)	
Pounds/in.(min.)	Warp 4.0 Fill 4.0

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 165.3 Fill 216.5

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 15.4 Fill 25.2

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 129.8 Fill 102.4

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	No change @ 60,000 cycles
Wyzenbeek, Cotton Duck	No change @ 400,000 cycles

Blocking (CFFA-4)	
	No. 1

W-Flex (CFFA-10)	
	25,000 cycles

Crock (CFFA-7)	
	Pass

UV (CFFA-2)	
QUV	650 hours

Mildew Resistance - ASTM G-21	
	1 mm Zone of Inhibition

Flame Retardancy	
California Tech. Bulletin 117	Pass
UFAC Fabric, Class 1	Pass

Miscellaneous

Application	
	Outdoor

Finish	
	PreFixx® Protective Coating



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com
contact us at upholstery@omnova.com

BOLTASOFT and PREFIX are registered trademarks of OMNOVA Solutions Inc.
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.
© 2007 OMNOVA Solutions Inc. 9/07
QA #: 015-20-128 • 09/21/05 • R: 1