

BoltaSoft® Marine Upholstery

Cabin Topping

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	17.40 ± 10%
Total Wt. – oz./lin. yd. (CFFA-700d)	27.0
Width (min.) – in. (CFFA-700a)	54"
Topskin Thickness	.0148"
Face Content	PVC

Backing	
Construction	Jersey Knit
Content	100% Polyester
Fiber Type	Spun

Adhesion (CFFA-3)	
Pounds/in.(min.)	Warp .95 Fill .88

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 94 Fill 48

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 39 Fill 24

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 61 Fill 38

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	3,000 cycles

Blocking (CFFA-4)	
	Pass 3

W-Flex (CFFA-10)	
	Pass 25,000 cycles

Crock (CFFA-7)	
	Pass

UV (CFFA-2)	
QUV	650 hours

Mildew Resistance - ASTM G-21	
	Pass

Flame Retardancy	
FMVSS-302	Pass

Miscellaneous

Application	
	Outdoor

Finish	
	Clear Vinyl



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com
contact us at upholstery@omnova.com

BOLTASOFT is a registered trademark of OMNOVA Solutions Inc.
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.
© 2007 OMNOVA Solutions Inc. 9/07
QA #: 015-11-155 • 09/21/05 • R: 0