

BoltaSoft® Marine Upholstery

Grand Cayman

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	20 ± 10%
Total Wt. – oz./lin. yd. (CFFA-700d)	30
Width (min.) – in. (CFFA-700a)	54"
Topskin Thickness	.007"
Face Content	PVC

Backing	
Construction	Terry Knit
Content	Polyester
Fiber Type	Filament

Adhesion (CFFA-3)	
Pounds/in.(min.)	Warp 4.0 Fill 4.0

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 85 Fill 75

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 20 Fill 27

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 35 Fill 30

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	No change @ 60,000 cycles
Wyzenbeek, Cotton Duck	No change @ 400,000 cycles

Blocking (CFFA-4)	
	No. 2 Max

W-Flex (CFFA-10)	
	25,000 cycles

Crock (CFFA-7)	
	20 cycles - no stain

UV (CFFA-2)	
QUV	650 hours

Mildew Resistance - ASTM G-21	
	Pass

Cold Crack (CFAA-6A)	
Roller Temperature	-20° F

Flame Retardancy	
FMVSS-302	Pass
California Tech. Bulletin 117	Pass
BIFMA	Pass
UFAC Fabric, Class 1	Pass

Miscellaneous

Application	
	Outdoor

Fogging (SAE J1756) % Reflect.	
	Pass 60 min.

Finish	
	PreFixx® Protective Finish



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com
contact us at upholstery@omnova.com

BOLTASOFT and PREFIXX are registered trademarks of OMNOVA Solutions Inc.
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.

© 2007 OMNOVA Solutions Inc. 9/07
QA #: 023-CP-180 • 09/21/05 • R: 1