

# BoltaSoft® Transportation Upholstery

## Novara

### Product Specifications:

<b>General</b>	
Total Wt. – oz./sq. yd. (CFFA-700d)	20.9 ± 10%
Total Wt. – oz./lin. yd. (CFFA-700d)	31.5
Width (min.) – in. (CFFA-700a)	54"
Topskin Thickness	.007"
Face Content	PVC

<b>Backing</b>	
Construction	Carded Knit
Content	Polyester/Rayon
Fiber Type	Spun

<b>Adhesion (CFFA-3)</b>	
Pounds/in.(min.)	Warp 3.0 Fill 3.0

<b>Tensile Strength (CFFA-17)</b>	
Pounds (min.)	Warp 85 Fill 75

<b>Trap Tear Strength (CFFA-16c)</b>	
Pounds	Warp 20 Fill 27

<b>Tack Strength (Stitch) (CFFA-14)</b>	
Pounds (min.)	Warp 35 Fill 30

### Performance Testing: meets or exceeds

<b>Abrasion (CFFA-1a)</b>	
Wyzenbeek, Wire Screen	Pass - 3,000 cycles

<b>Blocking (CFFA-4)</b>	
	No. 2

<b>W-Flex (CFFA-10)</b>	
	25,000 cycles

<b>Crock (CFFA-7)</b>	
	20 cycles - no stain

<b>UV (CFFA-2)</b>	
QUV	300 hours

<b>Mildew Resistance - ASTM G-21</b>	
	Pass

<b>Cold Crack (CFAA-6A)</b>	
Roller Temperature	-20° F

<b>Flame Retardancy</b>	
FMVSS-302	Pass
California Tech. Bulletin 117	Pass
BIFMA	Pass
UFAC Fabric, Class 1	Pass

### Miscellaneous

<b>Application</b>	
	Indoor

<b>Finish</b>	
	Urethane



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • [www.omnova.com](http://www.omnova.com)  
contact us at [upholstery@omnova.com](mailto:upholstery@omnova.com)

BOLTASOFT is a registered trademark of OMNOVA Solutions Inc.  
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA  
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT [WWW.OMNOVA.COM](http://WWW.OMNOVA.COM).  
© 2007 OMNOVA Solutions Inc. 9/07  
QA #: 023-CP-175 • 02/23/05 • R: 0