

PolyFox[®] Reactive Polymer Intermediates

Typical Physical Properties*

Property	PF-636	PF-6320	PF-656	PF-6520	PF-151N	PF-154N	PF-159	PF-7002
Polymer Type	Polyether Diol	Polyether Diol	Polyether Diol	Polyether Diol	Polyether Diol	Polyether Diol	Polyether Diol	Polyether Diol
Fluorinated side chain	-CF ₃	-CF ₃	-C ₂ F ₅	-C ₂ F ₅	-C ₂ F ₅	-C ₂ F ₅	-C ₂ F ₅	-C ₄ F ₉
DP [†]	6	20	6	20	6	6	6	4
wt% polymer	100	100	100	100	50	25	100	100
pH	6.0	6.0	6.5	7.0	4.5	4.5	4.5	6 - 7
Molecular Weight (g/mol)	1150	3480	1490	4480	2815	3464	3300	1670
wt% F (g F/100 g polymer)	27.6	29.9	34.7	39.3	24.5	19.5	15.4	46.0
Hydroxyl Functionality	di	di	di	di	di	di	di	di
Hydroxyl Equivalent Weight (g/mol)	564	1740	746	2240	1408	1732	1652	750
Hydroxyl Number (mg KOH/g)	99.5	32.2	75.2	25.0	39.9	32.4	34.0	67.2
Refractive Index	1.405	1.419	1.387	1.381	1.421	NA	1.435	1.385
Specific Gravity (lbs/gal)	10.0	10.2	10.6	10.9	9.7	8.8	9.5	11.3
Viscosity @ 77°F (cps)	1500	5300	2000	5800	700	50	1480	1500

Notes:

* Not actual product specifications

† Degree of Polymerization

NOTE:

Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such a use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.



OMNOVA Solutions Inc. · 1455 J. A. Cochran By-Pass. · Chester, SC 29706
Telephone (714) 273-9182 · www.omnova.com

POLYFOX is a registered trademark used under license by OMNOVA Solutions Inc.

ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM
© 2007 - 2010 OMNOVA Solutions Inc.
Rev. 03/09