



PolyFox™ Fluorosurfactant for Solvent Systems - Typical Physical Properties¹

Property	PF-636	PF-6320	PF-656	PF-6520	PF-651	PF-652
Polymer Type	Diol	Diol	Diol	Diol	Ethoxylated A-B diblock copolymer	Ethoxylated A-B-A triblock copolymer
Fluorinated side chain	- CF ₃	- CF ₃	- C ₂ F ₅	- C ₂ F ₅	- C ₂ F ₅	- C ₂ F ₅
DP ²	6	20	6	20	10	10
wt% polymer	100	100	100	100	50	50
wt% 2-propanol	0	0	0	0	50	50
pH	6.0	6.0	6.5	7.0	6.5 – 7.0	6.5 – 7.0
MW (approx.)	1150	3300	1425	4700	2975	3425
Refractive Index	1.405	1.419	1.387	1.381	1.465	1.465
Specific Gravity (lbs/gal)	10.0	10.2	10.6	10.9	8.1	8.1
Viscosity @ 77°F (cps)	2300	5500	1800	6900	40	100
Surface Tension (dyne/cm) ³	35.5	29.2	30.1	28.0	28	29

Notes:

¹ Not actual product specifications

² Degree of Polymerization

³ 1000 ppm (wt) active material in N-methylpyrrolidinone

NOTE:

Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such a use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.



OMNOVA Solutions Inc. · 1476 J. A. Cochran By-Pass. · Chester, SC 29706
Telephone (714) 273-9182 · www.omnova.com

POLYFOX is a trademark used under license by OMNOVA Solutions Inc.

ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM
© 2006-2010 OMNOVA Solutions Inc.
05-23-07