

SUNCRYL[®] 129 Vinyl Acrylic Copolymer Release Coating

SUNCRYL 129 release coating offers tight release, excellent solvent and high temperature resistance and develops excellent toughness after curing. Designed for hot melt, solvent-based natural rubber or water-based adhesives, **SUNCRYL 129** exhibits excellent mechanical stability and is low foaming; which enhances process efficiency and minimizes downtime.

<u>FEATURES</u>	<u>TYPICAL PROPERTIES</u>	
• Tight Release	pH:	4.0
• Excellent Solvent Resistance	Solids:	42%
• High Temperature Resistance	Density:	8.6 lbs/gal
• May be combined with Release Coatings at 10-30% addition, to tighten up tape overlap properties	Viscosity:	100 cps
	Tg:	+28°C
	Grit:	<20 ppm (200 mesh)

Comments: OMNOVA Solutions provides many release coat products designed for the tape industry. Because of the unique nature of tape products (adhesive selection, application techniques and use expectations, etc.), a wide variety of coatings have been developed. Please call your OMNOVA Solutions representative to discuss your particular tape release coating needs.

STORAGE AND HANDLING

- Recommended shelf life of 6 months; test to recertify release force
- Stir and mix well before using
- Protect from freezing
- Refer to Material Safety Data Sheets for additional details

NOTE:

Although data supplied above are believed to be accurate, each user is advised to make his or her own determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such a use will comply with all applicable laws or regulations, or whether such a use will not infringe the intellectual property rights of third parties.

Revised January 8, 2007

