

SUNCRYL[®] 154 Paper Tape Release Coating

SUNCRYL 154 release coating is designed for multipurpose creped paper masking tapes and provides moderate-to-tight release values for solvent-based (toluene) natural rubber, SIS-based and/or acrylic water-based adhesives.

<u>FEATURES</u>	<u>TYPICAL PROPERTIES</u>
<ul style="list-style-type: none">• Aqueous emulsion (no solvent emissions)	pH: 2.6 – 4.0
<ul style="list-style-type: none">• Clear coating	Solids: 41.0 – 43.0%
<ul style="list-style-type: none">• Moderate to tight release	Density: 9.0 lbs/gal (25°C)
<ul style="list-style-type: none">• Excellent mechanical stability	Viscosity: 300 - 500 cps RVT/25°C
<ul style="list-style-type: none">• Curable for solvent and humidity resistance	#2 spindle @ 20 rpm
<ul style="list-style-type: none">• Low foaming	Appearance: White emulsion

Comments: OMNOVA Solutions provides many primers and release products designed for the tape and label industry. Because the nature of tape and label products is influenced by the selection of adhesives, application techniques and use expectations, etc., a great variety of coatings has been developed. Please call your OMNOVA Solutions representative to discuss your particular primer or release coating needs.

STORAGE AND HANDLING

- Shelf life of 6 months (always test to recertify release force).
- Stir, mix well before using.
- Protect from freezing.
- Refer to Material Safety Data Sheets for additional details.

NOTE:

Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.

