

## SUNCRYL<sup>®</sup> CH 2200 Paper Tape Release Coating

**SUNCRYL CH 2200** release coating is designed for multipurpose creped paper masking tapes. **SUNCRYL CH 2200** is intended to offer easy-to-moderate release values for both solvent-based (toluene) natural rubber and/or SIS-based adhesives.

| <u>FEATURES</u>                                                                                                                                | <u>TYPICAL PROPERTIES</u>                                 |
|------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------|
| <ul style="list-style-type: none"><li>• Aqueous emulsion</li></ul>                                                                             | pH: 3.0 – 5.0                                             |
| <ul style="list-style-type: none"><li>• Less settling, easily dilutable</li></ul>                                                              | Solids: 39.0 – 43.0%                                      |
| <ul style="list-style-type: none"><li>• Clear coating</li></ul>                                                                                | Density: 8.9 lbs/gal<br>(25°C)                            |
| <ul style="list-style-type: none"><li>• Easy-to-medium release levels</li></ul>                                                                | Viscosity: <500 cps<br>RVT/25°C<br>#2 spindle @<br>20 rpm |
| <ul style="list-style-type: none"><li>• Compatible with Suncryl 3031 and Suncryl 129 to provide easier or tighter release properties</li></ul> |                                                           |
| <ul style="list-style-type: none"><li>• Curable for solvent and humidity resistance</li></ul>                                                  |                                                           |

**Comments:** OMNOVA Solutions provides many primers and release products designed for the tape and label industry. Because the nature of tape and label products is influenced by the selection of adhesives, application techniques and use expectations, etc., a great variety of coatings has been developed. Please call your OMNOVA Solutions representative to discuss your particular primer or release coating needs.

### STORAGE AND HANDLING

- Shelf life of 6 months (always test to recertify release force).
- Stir, mix well before using.
- Protect from freezing.
- Refer to Material Safety Data Sheets for additional details.

#### NOTE:

Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.



OMNOVA Solutions Inc. • 1455 J.A. Cochran Bypass • Chester, SC 29706  
Telephone • 803-385-5181 • [www.omnova.com](http://www.omnova.com)

SUNCRYL is a registered trademark of OMNOVA Solutions Inc.

ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT [WWW.OMNOVA.COM](http://WWW.OMNOVA.COM)  
©2010 OMNOVA Solutions Inc.  
March 2010