

SUNCRYL® CH 80 Paper Tape Release Coating

SUNCRYL CH 80 release coating is designed for multipurpose creped paper masking tapes. SUNCRYL CH 80 is intended to offer easy to medium release values for solvent-based (toluene) natural rubber and/or SIS based adhesives.

FEATURES

- Aqueous emulsion (no solvent emissions)
- Clear coating
- Easy to medium release levels
- Curable for solvent and humidity resistance

TYPICAL PROPERTIES

pH:	5.0
Solids:	41%
Density:	8.9 lbs/gal (25°C)
Viscosity:	<500 cps RVT/25°C #2 spindle @ 20 rpm

OMNOVA Solutions provides many release products designed for the tape industry. Because of the unique nature of tape products (adhesive selection, application techniques and use expectations, etc.), a great variety of coatings have been developed. Please call your OMNOVA Solutions representative to discuss your particular tape release coating needs.

STORAGE AND HANDLING

- Shelf life of 6 months, test to recertify release force
- Stir, mix well before using
- Protect from freezing
- Refer to Material Safety Data Sheets for additional details

NOTE:

Although data supplied above are believed to be accurate, each user is advised to make his or her own determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such a use will comply with all applicable laws or regulations, or whether such a use will not infringe the intellectual property rights of third parties.

Revised January 18, 2006



OMNOVA Solutions Inc. • 1476 J.A. Cochran ByPass • Chester, SC 29706
Telephone • 800-669-5236 • www.omnova.com

SUNCRYL is a registered trademark of OMNOVA Solutions Inc.

ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM
©2006 OMNOVA Solutions Inc.
04-26-06