

SUNCRYL[®] CL 223 B Paper Tape Release Coating

SUNCRYL CL 223 B release coating is designed for multipurpose creped paper masking tapes. **SUNCRYL CL 223 B** is intended to offer easy-to-moderate release values for both solvent-based (toluene) natural rubber and/or SIS-based adhesives.

<u>FEATURES</u>	<u>TYPICAL PROPERTIES</u>
• Aqueous emulsion (no solvent emissions)	pH: 3.0 – 5.0
• Clear coating	Solids: 40.0 – 42.0%
• Easy-to-medium release levels	Density: 8.9 lbs/gal (25°C)
• Curable for solvent and humidity resistance	Viscosity: <300 cps RVT/25°C #2 spindle @ 20 rpm

Comments: OMNOVA Solutions provides many primers and release products designed for the tape and label industry. Because the nature of tape and label products is influenced by the selection of adhesives, application techniques and use expectations, etc., a great variety of coatings has been developed. Please call your OMNOVA Solutions representative to discuss your particular primer or release coating needs.

STORAGE AND HANDLING

- Shelf life of 6 months (always test to recertify release force).
- Stir, mix well before using.
- Protect from freezing.
- Refer to Material Safety Data Sheets for additional details.

NOTE:

Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.

