

## SUNCRYL<sup>®</sup> CR 139 Paper Tape Release Coating

**SUNCRYL CR 139** release coating is designed for multipurpose creped paper masking tapes. **SUNCRYL CR 139** is intended to offer easy-to-moderate release values for both solvent-based (toluene) natural rubber and/or SIS-based adhesives.

<u>FEATURES</u>	<u>TYPICAL PROPERTIES</u>
<ul style="list-style-type: none"><li>• Aqueous emulsion (no solvent emissions)</li></ul>	pH: 6.5
<ul style="list-style-type: none"><li>• Rheology controlled for minimal strike-through</li></ul>	Solids: 32%
<ul style="list-style-type: none"><li>• Easy to medium release levels</li></ul>	Density: 8.9 lbs/gal (25°C)
<ul style="list-style-type: none"><li>• Curable for solvent and humidity resistance</li></ul>	Viscosity: 200 cps RVT/25°C #2 spindle @ 20 rpm

**Comments:** OMNOVA Solutions provides many release products designed for the tape industry. Because of the unique nature of tape products (adhesive selection, application techniques and use expectations, etc.), a wide variety of coatings have been developed. Please call your OMNOVA Solutions representative to discuss your particular tape release coating needs.

### STORAGE AND HANDLING

- Shelf life of 6 months, test to recertify release force
- Stir, mix well before using
- Protect from freezing
- Refer to Material Safety Data Sheets for additional details

**NOTE:**

Although data supplied above are believed to be accurate, each user is advised to make his or her own determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such a use will comply with all applicable laws or regulations, or whether such a use will not infringe the intellectual property rights of third parties.

Revised February 3, 2006.