



## SUNCRYL<sup>®</sup> CR 191 Non-Silicone Paper Tape Release Coating

**SUNCRYL CR 191** non-silicone release coating was designed for use with water based acrylic pressure sensitive adhesives to offer outstanding high speed unwind properties and excellent stability of release in aged masking tape products. **SUNCRYL CR 191** is intended to offer a tighter release than its counterpart - Suncryl CR 192.

### FEATURES

- Non-silicone aqueous emulsion (no solvent emissions)
- Clear coating intended for water based acrylic pressure sensitive adhesive masking tapes
- Tight release versus Suncryl CR 192
- Curable for solvent and humidity resistance

### TYPICAL PROPERTIES

pH:	7
Solids:	42%
Density:	9.0 lbs/gal (25°C)
Viscosity:	<500 cps RVT/25°C #2 spindle @ 20 rpm

**Comments: OMNOVA Solutions provides many release coat products designed for the tape industry. Because of the unique nature of tape products (adhesive selection, application techniques and use expectations, etc.), a wide variety of coatings have been developed. Please call your OMNOVA Solutions representative to discuss your particular tape release coating needs.**

### STORAGE AND HANDLING

- Recommended shelf life of 6 months; test to recertify release force
- Stir, mix well before using
- Protect from freezing
- Refer to Material Safety Data Sheets for additional details

#### NOTE:

Although data supplied above are believed to be accurate, each user is advised to make his or her own determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such a use will comply with all applicable laws or regulations, or whether such a use will not infringe the intellectual property rights of third parties.

Revised October 11, 2006

