

SUNCRYL® CR 192 Non-Silicone Paper Tape Release Coating

SUNCRYL CR 192 non-silicone release coating was designed for use with water-based acrylic pressure sensitive adhesives to offer outstanding high speed unwind properties and excellent stability of release in aged masking tape products. **SUNCRYL CR 192** offers a looser release than its counterpart - Suncryl CR 191.

| <u>FEATURES</u> | <u>TYPICAL PROPERTIES</u> |
|--|--|
| <ul style="list-style-type: none">• Non-silicone aqueous emulsion (no solvent emissions) | pH: 6.0 – 8.0 |
| <ul style="list-style-type: none">• Clear coating intended for water based acrylic pressure sensitive adhesive masking tapes | Solids: 41.0 – 43.0% |
| <ul style="list-style-type: none">• Loose release versus Suncryl CR 191 | Density: 9.0 lbs/gal (25°C) |
| <ul style="list-style-type: none">• Curable for solvent and humidity resistance | Viscosity: <500 cps RVT/25°C #2 spindle @ 20 rpm |

Comments: OMNOVA Solutions provides many primers and release products designed for the tape and label industry. Because the nature of tape and label products is influenced by the selection of adhesives, application techniques and use expectations, etc., a great variety of coatings has been developed. Please call your OMNOVA Solutions representative to discuss your particular primer or release coating needs.

STORAGE AND HANDLING

- Recommended shelf life of 6 months (always test to recertify release force).
- Stir, mix well before using.
- Protect from freezing.
- Refer to Material Safety Data Sheets for additional details.

NOTE:

Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.

