

# Boltaflex® Contract Upholstery

## Levanté

### Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	14.3 ± 10%
Total Wt. – oz./lin. yd. (CFFA-700d)	22.0
Width (min.) – in. (CFFA-700a)	.0099"
Face Content	PVC

Backing	
Construction	Non-Woven
Content	100% Polyester
Fiber Type	Staple

Adhesion (CFFA-3)	
Pounds/in.(min.)	Warp 4.0 Fill 4.0

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 80.5 Fill 78.2

Elongation @ 15# (CFFA-17)	
% (avg)	15% 25%

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 36.3 Fill 34.5

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 52.4 Fill 48.8

### Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	No change @ 60,000 cycles

Blocking (CFFA-4)	
	No. 1

W-Flex (CFFA-10)	
	Pass

Crock (CFFA-7)	
	Pass

UV (CFFA-2)	
QUV	40 hours indoors

Flame Retardancy	
California Tech. Bulletin 117	Pass
UFAC Fabric, Class 1	Pass

### Miscellaneous

Application	
	Indoor

Finish	
	PreFixx® Protective Coating



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • [www.omnova.com](http://www.omnova.com)  
contact us at [upholstery@omnova.com](mailto:upholstery@omnova.com)

BOLTAFLEX is a registered trademark of OMNOVA Solutions Inc.  
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA  
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT [WWW.OMNOVA.COM](http://WWW.OMNOVA.COM).

© 2007 OMNOVA Solutions Inc. 9/07  
QA #: 001-CG-008 • 10/11/06 • R: 1