

Boltaflex® Contract Upholstery

Touché

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	13.0 ± 0.5
Total Wt. – oz./lin. yd. (CFFA-700d)	19.5
Width (min.) – in. (CFFA-700a)	54"
Face Content	Urethane

Backing	
Construction	Brushed Woven
Content	Rayon
Fiber Type	Spun

Adhesion (CFFA-3)	
Pounds/in.(min.)	Warp 4.0 Fill 4.0

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 80 Fill 80

Elongation @ 15# (CFFA-17)	
% (avg)	Warp 4 ± 10% Fill 20 ± 10%

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 10 Fill 10

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 50 Fill 50

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	No change @ 30,000 cycles
Wyzenbeek, Cotton Duck	No change @ 200,000 cycles

Blocking (CFFA-4)	
	Pass

W-Flex (CFFA-10)	
	25,000 cycles

Crock (CFFA-7)	
	No color transfer

UV (CFFA-2)	
QUV	40 hours indoors

Cold Crack (CFAA-6A)	
Roller Temperature	-20° F

Flame Retardancy	
FMVSS-302	Pass
California Tech. Bulletin 117	Pass
UFAC Fabric, Class 1	Pass

Miscellaneous

Application	
	Indoor

Finish	
	Polyurethane



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com
contact us at upholstery@omnova.com

BOLTAFLEX is a registered trademark of OMNOVA Solutions Inc.
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.

© 2007 OMNOVA Solutions Inc. 9/07
QA #: 001-CG-008 • 10/11/06 • R: 1