

# Boltaflex<sup>®</sup> Contract Upholstery

## Vista

### Product Specifications:

#### General

Total Wt. - oz./sq. yd. (CFFA-700d)	18.7 ± 10%
Total Wt. - oz./lin. yd. (CFFA-700d)	28
Width (min.) - in. (CFFA-700a)	54"
Gauge (mils)	40 ± 10%
Face Content	PVC

#### Backing

Construction	Terry Loop Knit
Weight - oz./sq. yd.	3.7
Content	Polyester
Fiber Type	Filament

#### Adhesion (CFFA-3)

Pounds/Inches (min.)	Warp 4.0
	Fill 4.0

#### Tensile Strength (CFFA-17)

Pounds (min.)	Warp 85
	Fill 75

#### Trap Tear Strength (CFFA-16c)

Pounds (min.)	Warp 20
	Fill 27

#### Tack Strength (Stitch) (CFFA-14)

Pounds (min.)	Warp 35
	Fill 30

### Performance Testing: meets or exceeds

#### Abrasion

Wyzenbeek, Wire Screen	60,000 cycles
Wyzenbeek, Cotton Duck	1.3 million cycles

#### Blocking (CFFA-4)

No. 1

#### W-Flex (CFFA-10)

25,000 cycles

#### Crock (CFFA-7)

20 cycles - no stain

#### UV (CFFA-2)

QUV	650 hours (outdoors)
-----	----------------------

#### Mildew Resistance

ASTM G-21	Pass
-----------	------

#### Cold Crack (CFFA-6a)

-20°F

#### Flame Retardancy

California Tech. Bulletin 117	Pass
NFPA 701 Small Scale	Pass
Fed. Std. A-A-2950 Supercedes CCC-A-680A	Pass
FAR 25.853A	Pass
Boston Fire Dept. IX-1	Pass
NFPA 260	Pass
FMVSS-302	Pass
UFAC Fabric, Class 1	Pass

### Miscellaneous:

#### Application

Outdoor

#### Finish

PreFixx<sup>®</sup> Protective Coating



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com  
contact us at upholstery@omnova.com

BOLTAFLEX and PREFIX are registered trademarks of OMNOVA Solutions Inc.  
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA  
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM  
© 2010 OMNOVA Solutions Inc. QA#007-CP-0150 Rev.4 • 08/04/08