

Boltaflex® Contract Upholstery

Capitano

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	19.5 ± 10%
Total Wt. – oz./lin. yd. (CFFA-700d)	29.25
Width (min.) – in. (CFFA-700a)	54.5"
Topskin Thickness	.006"
Face Content	PVC

Backing	
Construction	Knit
Content	Polyester
Fiber Type	Filament

Adhesion (CFFA-3)	
Pounds/in.(min.)	Warp 3.0 Fill 3.0

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 85 Fill 75

Elongation @ 15# (CFFA-17)	
% (min)	Warp 8 Fill 18

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 20 Fill 20

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 35 Fill 30

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	6,000 cycles

Blocking (CFFA-4)	
	No. 1

W-Flex (CFFA-10)	
	25,000 cycles

Crock (CFFA-7)	
	20 cycles - no stain

QUV (CFFA-2)	
	650 hours - no change

Mildew Resistance - ASTM G-21	
	Pass

Flame Retardancy	
California Tech. Bulletin 117	Pass
UFAC Fabric, Class 1	Pass

Miscellaneous

Application	
	Outdoor

Finish	
	Clear Vinyl



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com
contact us at upholstery@omnova.com

BOLTAFLEX is a registered trademark of OMNOVA Solutions Inc.
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.
© 2007 OMNOVA Solutions Inc. 09/07
QA #: 015-CP-015 • 08/09/06 • R: 2