

BoltaSoft® Aftermarket Upholstery

Black

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	18 ± 10%
Total Wt. – oz./lin. yd. (CFFA-700d)	27
Width (min.) – in. (CFFA-700a)	54"
Gauge	.039" ± 2%
Topskin Thickness	.005"
Face Content	Vinyl

Backing	
Construction	Knit
Weight – oz./sq. yd.	2.6
Content	Polyester
Fiber Type	Filament

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	Pass – 6,000 cycles

Blocking (CFFA-4)	
	No. 1

W-Flex (CFFA-10)	
	25,000 cycles

Crock (CFFA-7)	
	20 cycles – no stain

QUV	
	200 hours

Adhesion (CFFA-3)	
Pounds/Inches (min.)	Warp 3 Fill 3

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 75 Fill 75

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 20 Fill 20

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 30 Fill 30

Cold Crack (CFFA-6a)	
Roller Temperature	-10°F

Flame Retardancy	
FMVSS-302	Pass
California Tech. Bulletin 117	Pass
UFAC Fabric, Class 1	Pass

Miscellaneous

Application	
	Indoor

Finish	
	Clear Vinyl (CV) Coating



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com
contact us at upholstery@omnova.com

BOLTASOFT is a registered trademark of OMNOVA Solutions Inc.
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.
© 2005 OMNOVA Solutions Inc.
QA #: 001-CP-015 • 02/04/05 • R: 0