

Nautolex[®] Marine Upholstery

DuraTouch

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	13.0 ± 0.5
Total Wt. – oz./lin. yd. (CFFA-700d)	19.5
Width (min.) – in. (CFFA-700a)	53"
Face Content	Urethane

Backing	
Construction	Woven
Content	Rayon
Fiber Type	Spun

Adhesion (CFFA-3)	
Pounds/Inches (min.)	Warp 5.0 Fill 5.0

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 95 Fill 95

Elongation @ 15# (CFFA-17)	
(min)	Warp 4% ± 10% Fill 25% ± 10%

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 15 Fill 15

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 70 Fill 70

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	No change @ 30,000 cycles

Blocking (CFFA-4)	
	Pass

W-Flex (CFFA-10)	
	Pass – 25,000 cycles

Crook (CFFA-7)	
	No color transfer

QUV – Indoor	
	100 hours

Flame Retardancy	
FMVSS-302	Pass
California Tech. Bulletin 117	Pass
UFAC Fabric, Class 1	Pass

Miscellaneous

Application	
	Indoor

Finish	
	None



OMNOVA Solutions Inc. • Fairlawn, OH 44333 • www.omnova.com
contact us at upholstery@omnova.com

NAUTOLEX is a registered trademark of OMNOVA Solutions Inc.
ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA
STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.
© 2005 OMNOVA Solutions Inc.
03/22/05 • R: 0