Boltaflex Vista

Featuring a pebbled leather grain, Vista has been styled for broad market appeal along with it's coordinates Venue and Vivo for healthcare, hospitality, marine and recreational vehicle applications.

Protected with **PreFixx** protective finish, *Vista* has been engineered to be cleaned and disinfected with a wide variety of chemical cleaners without worrying about discoloration or damage to the upholstery finish when the recommended cleaning process is followed.

Industries & Markets

- · Corporate Office
- Food Service
- Healthcare
- · Hospitality & Entertainment
- Retail
- · Recreational Vehicles

End-Use Applications

- Contract Seating
- Dining Seating
- Medical Furnishings
- · Guest room furnishings
- Lobby furnishings & millwork
- Spas & Health Clubs
- Theater Seating
- · Retail Seating
- Interior Surfaces

Physical Specifications

Weight (CFFA-700d)	28 oz/lin yd [18.7 oz/yd²]
Weight, Metric (CFFA-700d)	849 g/lin m [619 g/m²]
Width (CFFA-700a)	54 in. [137 cm]
Face Composition	PVC
Backing Description	Polyester Terry Loop Knit
Roll Size	40 lin yd [37 lin m]
Emboss Level	Medium
Shipping Weight/ Roll	68 lb [31 kg]

Flame, Smoke & Toxicity

Meets or exceeds the following:		BIFMA - Class A
	•	Boston Fire Dept IX 1
	•	Cal Tech 117-2013 Sec 1
	•	FAR 25.853a & Appx F Part 1 (a)(1)(ii)
	•	FMVSS-302
	•	IMO Part 8 Upholstered Furniture 3.1 Smoldering Cigarette
	•	IMO Part 8 Uphlstered Furniture 3.2 Propane Flame
		NFPA 701 Small Scale
	•	NFPA 260, Class 1
		Port Authority of NY/NJ
		UFAC Fabric, Class 1
	•	Federal Spec CID A-A-2950-A
	•	ASTM E-84

Performance Features

Use Indoor/Outdoor QUV hours (minimum) 650 Adhesion #/in., min (CFFA-3) 4 Warp, 4 Fill	
Adhesion #/in., min (CFFA-3) 4 Warp, 4 Fill	
7 7 7 7	
Tensile Strength #, min (CFFA-17) 85 Warp, 75 Fill	
Tack Strength #, min (CFFA-14) 35 Warp, 30 Fill	
Trap Tear Strength #, min (CFFA-16c) 20 Warp, 27 Fill	
Wyzenbeek Abrasion (CFFA-1a) 1,300,000 Cotton Duck (doub	ple rubs)
Blocking (CFFA-4 No. 1) Pass	
W-Flex - 25,000 cycles (CFFA-10) Pass	
Crocking Resistance - 20 cycles no stain (CFFA-7)	
Fungal Resistance (ASTM-G-21) Pass	
Bacterial Resistance (AATCC 147) Pass	
Bacterial Resistance (AATCC 100) Pass	
Cold Crack (CFFA-6a) -20 °F [-29 °C]	
Slit Tear Resistance (ASTM D2212-00) Pass	
Puncture Resistance (ASTM D4833-07) Pass	
Compatible with Disinfectants Yes. See Chem Resistance Te	ech Bulletin for more information.
Bleach-Safe Yes, 10% Bleach Solution	
Surface Resistance - anti-static Yes (AATCC-76)	
Resistance to Sulfide Stain (ASTM D1712) Yes	
Oil Resistance (CFFA-13) Yes	
Urine Resistance (AATCC-6) Yes	

Revision Date: 15-August-22

Note: Due to possible variances in your computer monitor, the colors and patterns displayed may vary slightly from the actual product. Customers should always obtain and compare actual samples before specifying.



North American Headquarters

OMNOVA Solutions Inc. 25435 Harvard Road Beachwood, OH 44122-6201 USA

Phone: +1 216-682-7000 Email: upholstery@omnova.com Thailand Manufacturing Plant

111/7 Moo 2, T. Nikompattana Amphur Nikompattana Rayong 21180, Thailand Phone: +011-66-38-897103 Fax: +011-66-38-637749

All OMNOVA products and services are offered and sold subject to the OMNOVA standard terms and conditions of sale agreement set forth at www.omnova.com

Trademarks are property of OMNOVA Solutions Inc. unless otherwise noted. ©2022 OMNOVA Solutions
OMNOVA - A Division of SURTECO.