

Car Bra is a heavy-duty vinyl coated fabric used in the fabrication of automotive protective coverings.

Industries & Markets

- Automotive

End-Use Applications

- Aftermarket Upholstery

Physical Specifications

Weight (CFFA-700d)	33 oz/lin yd [22 oz/yd ²]
Weight, Metric (CFFA-700d)	1,023 g/lin m [750 g/m ²]
Width (CFFA-700a)	55 in. [140 cm]
Face Composition	PVC
Backing Description	Polyester Nonwoven
Roll Size	50 lin yd [46 lin m]
Emboss Level	Light
Shipping Weight/ Roll	106 lb [48 kg]

Flame, Smoke & Toxicity

- Meets or exceeds the following:
- Cal Tech 117-2013 Sec 1
 - UFAC Fabric, Class 1

Performance Features

Protective Finish	Clear Vinyl
Use	Indoor/Outdoor
QUV hours (minimum)	650
Adhesion #/in., min (CFFA-3)	9 Warp, 8 Fill
Tensile Strength #, min (CFFA-17)	199 Warp, 237 Fill
Tack Strength #, min (CFFA-14)	103 Warp, 104 Fill
Trap Tear Strength #, min (CFFA-16c)	96 Warp, 105 Fill
Wyzenbeek Abrasion (CFFA-1a)	6,000 Wirescreen (double rubs)
Blocking (CFFA-4 No. 1)	Pass
W-Flex - 25,000 cycles (CFFA-10)	Pass
Crocking Resistance - 20 cycles no stain (CFFA-7)	Pass
Fungal Resistance (ASTM-G-21)	Pass
Cold Crack (CFFA-6a)	-20 °F [-29 °C]

Revision Date: 03-Oct-19

Note: Due to possible variances in your computer monitor, the colors and patterns displayed may vary slightly from the actual product. Customers should always obtain and compare actual samples before specifying.



World Headquarters
OMNOVA Solutions Inc.
25435 Harvard Road
Beachwood, OH 44122-6201
USA
Phone: +1 216-682-7000
Email: upholstery@omnova.com

Thailand Manufacturing Plant
111/7 Moo 2, T. Nikompattana
Amphur Nikompattana
Rayong 21180, Thailand
Phone: +011-66-38-897103
Fax: +011-66-38-637749

All OMNOVA products and services are offered and sold subject to the OMNOVA standard terms and conditions of sale agreement set forth at www.omnova.com

Trademarks are property of OMNOVA Solutions Inc. unless otherwise noted.

©2019 OMNOVA Solutions Inc.